

TRICOLENE LLB2918

Linear Low Density Polyethylene

777 Post Oak Blvd, Suite 550,
Houston TX, USA - 77056
+1-713-963-0066
www.triconenergy.com



ADDING A WORLD OF VALUE

PRODUCT DESCRIPTION

This type of LLDPE is a copolymer of ethylene and 1-butene produced with Ziegler-Natta catalysts in a gas phase polymerization process.

PROCESSING METHODS

Blown Film (Co)Extrusion
Cast Film (Co)Extrusion

CHARACTERISTICS

Gloss and Drawdown

APPLICATIONS

Cast Stretch Film
Hygiene Film
Cast and Blown Film for Packaging

RESIN PROPERTIES

	TEST METHOD	VALUES, ENGLISH UNITS	VALUES, INTERNATIONAL UNITS
Melt Flow Rate 2.16 kgf/190 °C MFR ₂	ASTM D1238	2.0 g/10 min	2.0 g/10 min
Density 23 °C	ASTM D1505	0.918 g/cm ³	0.918 g/cm ³
Antioxidant Package	---	Yes	Yes

FILM PROPERTIES *

	TEST METHOD	VALUES, ENGLISH UNITS	VALUES, INTERNATIONAL UNITS
Evaluated Film Thickness	---	0.8 mils	20.3 μm
Dart Impact Strength 38.0 mm (1.5 in), 0.66 m (26.0 in), F50	ASTM D1709A	50 g	50 g
Elmendorf Tear Strength	ASTM D1922	MD 20 g TD 430 g	20 g 430 g
Tensile Strength at Yield 20.0 in/min (508 mm/min)	ASTM D882	MD 1,100 psi TD 940 psi	8 MPa 6 MPa
Tensile Strength at Break 20.0 in/min (508 mm/min)	ASTM D882	MD 9,000 psi TD 3,600 psi	62 MPa 25 MPa
Tensile Elongation at Break 20.0 in/min (508 mm/min)	ASTM D882	MD 420 % TD 830 %	420 % 830 %
Tensile Secant Modulus of Elasticity 1 % Elongation, 0,051 in/min (1,3 mm/min)	ASTM D882	MD 17,000 psi TD 19,000 psi	117 MPa 131 MPa
Haze	ASTM D1003	1.7 %	1.7 %
Specular Gloss 45 °	ASTM D2457	98.0	98.0

PROCESSING CONDITIONS OF THE EVALUATED FILM

	TEST METHOD	VALUES, ENGLISH UNITS	VALUES, INTERNATIONAL UNITS
Die Width		3.5 in	89 mm
Melt Temperature		534 ° F	279 ° C
Chill Roll Temperature		80 ° F	27 ° C
Take-off Speed		750.0 ft/min	228.7 m/min

* The data presented here is true and accurate to the best of our knowledge. Likewise, the values are nominal and should not be taken as minimum or maximum specifications.
No warranty, express or implied, is made regarding resin performance. The customer must validate these properties according to his own evaluations on his machine and in his laboratory.

REGULATORY COMPLIANCE

This resin complies with the following FDA regulation: 21 CFR 177.1520: Olefinic Polymers. This regulation describes polyolefin resins that can be used safely for food packaging and preservation at low temperatures and at ambient temperatures. This resin is not designed for use in medical applications and should not be used in such applications.